



Galax Quarry

3rd Quarter 2022

Specific Gravity: 2.786

L.A. Abrasion (%): 21.8

Soundness: 13.7

Average Gradation Percent Passing

Course Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16	#50	#100	#200
57			100.00%	100.00%	92.85%	25.61%	6.08%	2.92%	2.38%				

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				99.54%	91.86%	73.05%	60.29%	39.50%				