



Shawsville Quarry

4th Quarter 2022

Specific Gravity: 2.8

L.A. Abrasion (%): 18.4

Soundness: 0.5

Average Gradation Percent Passing

Course Aggregate

Sieve Size	3 1/2"	3"	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#8	#16
57					100.00%	100.00%	100.00%	36.20%	36.20%	4.03%	2.28%	
68						100.00%	100.00%	100.00%	47.77%	8.18%	5.52%	3.49%
78							100.0%	94.2%	65.7%	4.7%	2.2%	1.9%
8								100.0%	95.1%	28.6%	1.9%	1.3%

Dense Graded Aggregate

Sieve Size	2 1/2"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	#4	#10	#16	#40	#200
26				100.00%	94.20%	94.20%	94.20%	37.90%				